

**PROJECT:** Product Check

**CLIENT:** Pasco Mine

# LIMEROCK BEARING RATIO TEST

**TEST METHOD:** FDOT FM 5-515

**PROJECT NO:** 1505.21.1

**DATE:** July 7, 2025

**LAB NO:** B-15425

**LBR TEST NO:** 29

**COMPACTION TEST NO.:** 49

**MAXIMUM LBR VALUE (%):** 128

**MAXIMUM DRY DENSITY (PCF):** 122.4

**OPTIMUM MOISTURE (%):** 9.7

**DATE RECEIVED:** 06/20/25

**DATE TESTED:** 07/05/25

**TESTED BY:** MD

**LOCATION SAMPLED:** Stockpile

**SOIL DESCRIPTION:** Crushed Limerock



**TYPE OF MATERIAL:** Base

**SOAKING TIME (HRS):** 48±4

**SOAKING SURCHARGE (LBS):** 2.5

**TESTING SURCHARGE (LBS):** 0

**REMARKS:**



**SHANNON R. SNYDER, P.E.**

Florida License No. 57019

This report contains information that is intended solely for the use of the client and noted assigns.

This report shall not be reproduced, except in full, without written approval of Test Lab, Inc.